

91115
IN-03-02
170797
p-8

Final Technical Report

NASA Project (NAG-1-1250)

"New Aromatic Activated Dihalides and Bisphenol Monomers
for the Preparation of Novel Poly(arylene ethers)"

Prepared for

Materials Division and Structures and Dynamics Division
National Aeronautics and Space Administration
Langley Research Center
Hampton, Virginia 23665

Prepared by

Dr. James F. Wolfe
Vice Provost for Academic Affairs
and Professor of Chemistry
Virginia Polytechnic Institute and State University
Blacksburg, VA 24061

Date of Preparation
June 7, 1993

N94-10513

Unclass

G3/23 0170797


(NASA-CR-193190) NEW AROMATIC
ACTIVATED DIHALIDES AND BISPHENOL
MONOMERS FOR THE PREPARATION OF
NOVEL POLY(ARYLENE ETHERS)
(Virginia Polytechnic Inst. and
State Univ.) 8 p

Introduction







This final report summarizes the technical achievements resulting from research activities supported during the tenure of this grant (06/01/91 - 09/30/92).


Technical Achievements

The goal of this research program was to synthesize a series of unique monomers of type I to be utilized at NASA-Langley in the preparation of new poly(arylene ether ketones), poly(arylene ether ketosulfones), and poly(arylene ether ketophosphine oxides). These A-A and A-B monomer systems, which possess activated aryl halide and/or phenolic end groups, are accessible via condensation reactions of appropriately substituted aryl acetonitrile carbanions with activated aryl dihalides followed by oxidative decyanation.




Monomer





I. Synthesis of Monomers 3a-d

The general synthetic route for the preparation of monomers 3a-d involved the condensation of excess α -lithio-4-fluorophenylacetonitrile, prepared from the nitrile and *n*-BuLi, with the appropriate activated aryl dihalide to give intermediate bis-nitriles 2a-d, followed by phase transfer-catalyzed oxidative decyanation. (Scheme I).




Overall yields in this two step process were >80% and satisfactory combustion analyses were obtained for all but phosphine oxide monomer **3b**. In reactions to prepare dinitrile **2b**, an inseparable mixture of **2b** along with some of the monosubstitution product was invariably obtained. This same nitrile mixture persisted even when the difluoro analogue of **1b** was treated with excess α -lithio-4-fluorophenylacetonitrile for 12 h in refluxing THF. Surprisingly, a similar reaction using excess α -lithio-4-fluorophenylacetonitrile, generated using lithium diisopropylamide (LDA) as the base, gave only the monosubstitution product. Subsequent oxidative decyanation of this mixture afforded a mixture of ketone monomers from which it was impossible to obtain pure **3b** by column chromatography.

II. Synthesis of Monomers 6 and 9

Monomers **6** and **9** were prepared in overall yields of 90% and 73%, respectively, starting with, condensation of bis-(4-chlorophenyl)sulfone (**1a**) and α -lithio-4-methoxyphenylacetonitrile. (Scheme II).

Scheme II




Although an alternative synthesis of monomer **9** was also accomplished beginning with condensation of **1a** with α -lithio-4-fluorophenylacetonitrile, overall yields of **9** by this route were lower than with α -lithio-4-methoxyphenylacetonitrile.

III. Synthesis of Monomer **13**

The preparation of the nitrile precursor, **12**, of monomer **13** turned out to be rather difficult. Attempted one-pot syntheses of **12** involving the stepwise addition of two 1-equiv portions of **1a**, first to 2 equiv of α -lithioacetonitrile and then to α -lithionitrile **11**, formed *in situ*, gave a mixture of nitrile products consisting of **10**, **12** and bis-(4-cyanomethylphenyl) sulfone, which made the isolation of **12** very inefficient. Ultimately, the two step reaction shown in Scheme III proved to be satisfactory for the preparation of **12**. Thus, nitrile **10** was isolated

Scheme III




in 80% yield from the reaction of **1a** with α -lithioacetonitrile. The subsequent condensation reaction to prepare **12** which proceeded very sluggishly due to the weakly nucleophilic nature of carbanion **11**, afforded nitrile **12** in yields ranging from 70-75% based on reacted **10**. When an

additional equivalent of *n*-BuLi was employed in this reaction to improve the conversion of **10** by regenerating carbanion **11** consumed during the course of the reaction via protonation by **12**, a complex reaction mixture resulted, which still contained a substantial quantity of unreacted **10**. Similar results were obtained when 2 equiv of lithium diisopropylamide (LDA) was used as the base in place of *n*-BuLi. Oxidative decyanation of **12** required inordinately long reaction times (three to four days) for completion (87% yield of **13**) presumably as a result of the low reactivity of the highly delocalized nitrile carbanion with oxygen.

IV. Synthesis of Monomers **17** and **19**


The synthesis of monomer **17** from sulfone **1a** and 1,3-phenylenediacetonitrile (**14**) is outlined in Scheme IV.

Scheme IV



Stepwise condensation of 2 equiv of **1a** with α,α' -dilithio-1,3-phenylenediacetonitrile (**15**) afforded a 72% yield of dinitrile **16**. Phase transfer-catalyzed oxidative decyanation of **16**, which required a two day reaction period, gave analytically pure monomer **17** in 76% yield.

When the same synthetic approach used to synthesize monomer **17** was applied to the preparation of monomer **19**, some unexpected difficulties were encountered. Attempted synthesis of intermediate dinitrile **18** by addition of sulfone **1a** to a solution of α,α' -dilithio-1,4-phenylenediacetonitrile at -78°C yielded a solid material (polymer?) which was essentially



insoluble in organic solvents. By reversing the order of addition and thus maintaining an excess of **1a**, this problem was avoided and pure dinitrile **18** was obtained in 67% yield. The conversion of **18** to monomer **19**, however, also proved to be problematical. Unlike its dinitrile analogue **16**, **18** was virtually insoluble in toluene, the organic solvent employed in all previous oxidative decyanation reactions in this study. As a result, this reaction proceeded very slowly and after several days gave a solid product mixture having very limited solubility in organic solvents. Subsequently, several other solvent/base systems were employed, including THF/*n*-BuLi, DMSO/LDA, DMSO/NaOH, and dioxane/LDA, but the same intractable reaction mixture persisted in each case. Regrettably, after about a three month effort, we were unable to obtain monomer **19** in the high degree of purity required for use in polymer synthesis. The purest material we were able to isolate melted at $297\text{--}300^\circ\text{C}$ and analyzed 0.7% high in hydrogen.

Samples of the seven monomers listed in Table I whose syntheses are previously described in this report were submitted to Paul Hergenrother at the NASA-Langley Research Center for the

preparation of new poly(arylene ethers). Several moderately high molecular weight polymers of this type have been prepared and evaluation of these materials is continuing.

Table I

Monomer*	Quantity (g)	M.P.°C
3a	13	183-184
3c	13	342-343
3d	20	309-310
6	18	226-227
9	20	198-199
13	14	226-227
17	20	232-233

* Combustion analyses for all monomers were within 0.4% of theoretical values. ¹H NMR spectrum were in agreement with assigned structures and purity.

Personnel Supported

Dr. Graciela Bariberi, Ph.D. Virginia Tech, Research Associate, 02/01/91 - 08/31/91

Dr. Phuoc Nguyen, Ph.D. Northeastern University, Research Associate, 10/01/91 - 11/30/92